Technical & General

tgzoe 1

Instruction for Use

Z.O.E. CEMENT

Z.O.E Cement is an improved Zinc Oxide Eugenol Cement with a setting time of from 6 to 8 minutes. It is recommended for lining cavities in posterior and anterior teeth (not under acrylic filling materials), for temporary cementation, and as a sedative base under metallic restorations.

Z.O.E Cement protects the pulp from thermal shock and possible irritation from freshly mixed cements. Cavities lined with Z.O.E Cement may be filled promptly.

DIRECTIONS FOR USE.

For convenient mixing and cleanliness, mixing pads are preferred to a glass slab. Always use a stainless steel spatula. Use a mixing ratio of 1.4 grams of powder to 0.4 ml liquid.

Place the suggested quantities of powder and liquid on the mixing tablet. Divide the powder into four equal portions which are to be successively added to the liquid. Spatulate each addition until the mix will be complete and rather stiff in 1 ½ minutes.

For Professional Dental use only

CE 2862

Technical & General Ltd.
2 Albion PI, London W6 0QT, United Kingdom
Tel: +44 20 8834 7575 Fax: +44 20 8834 7570
www.tgdent.com

VAT GB: 448 8016 3
21JUL25
ZO T1
Registered in England: 1995369
Version 5

TECHNICAL & GENERAL Ltd.
WARNINGS

Intention for use in for lining cavities in posterior and anterior teeth (not under acrylic filling materials), for temporary cementation.

Composition:
Zinc oxide
Eugenol
Hardener

The z.o.e. cement is not irritable to the skin. In case of contact with the eyes, wash immediately with abundant water for at least 15 minutes and if the irritation still persist consult a doctor. In case of contact with skin wash the area with soap and water. In case of inhalation clean the nose with water and seek medical assistance. Before the use of these products always use rubber dam.

Some patients can present allergy to the z.o.e. cement or any of its components. In this case stop its use. Do not store at temperature above 24°C. Close the packages immediately after dispensing of the product.

Keep out of reach of children.
For professional dental use only.

Contraindication: The material must not be used when the application techniques described are not possible.

Warranty: Technical & General Ltd. Warrants the product against any fault of manufacture of the material. Technical & General Ltd., does not take responsibility for the misuse of the product out of the intention for use specified or out of the instructions for use, or out of the precautions, the warnings, and indicated contraindications. Being the only obligation is the replacement of the defective product.

Information: Post-production:
If the use of these products on a patient or any one else causes some anomaly, please send detailed report to Technical & General Ltd.



CONAMCO, S.A. de C.V.
José María Bustillos No. 28 Bis, 1er y 2do piso.
Colonia Algarín, Delegación Cuauhtémoc, CP.
Ciudad de México, 06880, Mexico

EU REP **Ivonne Richaud.**
Travessera de Gracia, 315, 2°-1° 08025
Barcelone, Spain

NO REFRIGERATION NECESSARY